

DUAL REFLECTIVE SPECIFICATION

	Visible Light %			Rejection %				Solar Energy			Structure	
	Transmitted	Exterior Reflection	Interior Reflection	IRR (900~1000nm)	IRR (780~2800nm)	UV Rays	TSER	Transmitted	Reflection	Absorbed	Ply	Mil
Dual 15	15	48	21	90	90	>99	75	15	47	39	2	2
Dual 25	25	27	14	82	80	>99	60	28	29	44	2	2
Dual 35	35	27	14	48	45	>99	45	42	14	44	2	2