

PREMIUM CERAMIC IR SPECIFICATION

	Visible Light %			Rejection %				Solar Energy			Structure	
	Transmitted	Exterior Reflection	Interior Reflection	IRR (900~1000nm)	IRR (780~2800nm)	UV Rays	TSER	Transmitted	Reflection	Absorbed	Ply	Mil
Premium 5	5	7	6	76	89	>99	66	12	7	81	2	1.5
Premium 15	15	8	6	71	85		62	22	8	70		
Premium 20	20	6	6	71	84		60	24	6	70		
Premium 35	35	9	7	71	83		58	31	8	61		
Premium 40	40	9	8	71	82		54	36	8	56		
Premium 50	50	10	8	73	79		51	41	8	50		
Premium 70	70	10	10	71	83		47	47	9	44		