

SILVER REFLECTIVE SPECIFICATION

	Visible Light %			Rejection %				Solar Energy			Structure	
	Transmitted	Exterior Reflection	Interior Reflection	IRR (900~1000nm)	IRR (780~2800nm)	UV Rays	TSER	Transmitted	Reflection	Absorbed	Ply	Mil
Silver 15	15	60	64	85	93	>99	78	14	14	26	2	1.5
Silver 35	35	39	40	71	81	>99	61	29	39	31	2	1.5